

CAD-CUT® Glitter Flake™ Heat Transfer Vinyl

Application Instructions

Application to Natural Fibers

Time:

10-12 seconds

Temperature:

302°F/150°C

Pressure:

Medium

Peel:

Hot

Application to Synthetic Fibers

Time:

10-12 seconds

Temperature:

290°F/143°C

Pressure:

Medium

Peel:

Hot

Heated Lower Platen Application to 100% Polyester

Lower Platen:

320°F

Upper Platen:

270°F

Time:

10 seconds

Pressure:

60 psi (#6/Medium on Hotronix® machines)

Heated Lower Platen Instructions for 95% Polyester / 5% Spandex /

Triblends

Lower Platen:

290°

Upper Platen:

270°

Time:

30 secs

Pressure:

60 psi (#6/Medium on Hotronix®)

Material/Fabric Compatibility

- 100% Cotton
- 100% Polyester
- 100% Preshrunk Cotton

- Cotton/Poly Blends

Special Notes

When Light Pink Glitter Flake is applied to dark colored fabrics, the light pink color becomes iridescent.

Power Platen not recommended for use with 100% cotton fabrics. For blends with high cotton content proceed with caution. Test application using upper heat only, if it scorches test using lower heat. Decrease pressure for smaller Power Platen sizes.

Care Instructions

Machine wash inside-out using mild detergent.

Do not use bleach. Dry at a normal dryer setting on household machines. Do not dry clean.

Storage

Store in a cool and dry area around 65 to 70 degrees Fahrenheit with 50% relative humidity. Keep away from direct heat, sunlight and humidity. Recommended shelf life is one year.

Note

The recommended time, temperature, and pressure settings are for Stahls' Hotronix® heat press machines. Settings on other heat presses may vary.